

MATERIAL SAFETY DATA SHEET

PG 48093 RD PP

Version Number 1.0 Revision Date 01/09/2004

Page 1 of 6 Print Date *11/13/2011*

1. PRODUCT AND COMPANY IDENTIFICATION

POLYONE CORPORATION 33587 Walker Road, Avon Lake, OH 44012

NON-EMERGENCY TELEPHONE	:	Product Stewardship (770) 271-5902
Emergency telephone number	:	CHEMTREC 1-800-424-9300 (24hrs for spill, leak, fire, exposure or accident).
Product name	:	PG 48093 RD PP
Product code	:	CC10048093
Chemical Name	:	Mixture
CAS-No.	:	Mixture
Product Use	:	Industrial Applications

2. COMPOSITION/INFORMATION ON INGREDIENTS

Components	CAS-No.	Weight %
Silica, amorphous, precipitated and gel	112926-00-8	1 - 5

3. HAZARDS IDENTIFICATION

EMERGENCY OVERVIEW

This mixture has not been evaluated as a whole. Information provided on the health effects of this product is based on individual components. All ingredients are bound and potential for hazardous exposure as shipped is minimal. However, some vapors may be released upon heating and the end-user (fabricator) must take the necessary precautions (mechanical ventilation, respiratory protection, etc.) to protect employees from exposure.

POTENTIAL HEALTH EFFECTS

Routes of Exposure:	: Inhalation, Ingestion, Skin contact
Acute exposure	
Inhalation Ingestion Eyes	 Resin particles, like other inert materials, can be mechanically irritating. May be harmful if swallowed. Resin particles, like other inert materials, are mechanically irritating to eyes.
Skin	: Experience shows no unusual dermatitis hazard from routine handling.
Chronic exposure	: Refer to Section 11 for Toxicological Information.
Medical Conditions Aggravated by Exposure:	: None known.



MATERIAL SAFETY DATA SHEET **PG 48093 RD PP**

Version Number 1.0 Revision Date 01/09/2004 Page 2 of 6 Print Date 11/13/2011

	4. FIRST AID MEASURES
Inhalation	: Move to fresh air in case of accidental inhalation of fumes from overheating or combustion. When symptoms persist or in all cases of doubt seek medical advice.
Ingestion	: Do not induce vomiting without medical advice. When symptoms persist or in all cases of doubt seek medical advice.
Eyes	: Rinse immediately with plenty of water, also under the eyelids, for a least 15 minutes. If eye irritation persists, seek medical attention.
Skin	: Wash off with soap and plenty of water. If skin irritation persists see medical attention.
	5. FIRE-FIGHTING MEASURES
Flash point	: Not applicable
Flammable Limits	
Upper explosion limit	: Not applicable
Lower explosion limit	: Not applicable
Autoignition temperature	: Not applicable
Suitable extinguishing media	: Carbon dioxide blanket, water spray, dry powder, foamnone.
Special Fire Fighting Procedures	: Fullface self-contained breathing apparatus (SCBA) used in positive pressure mode should be worn to prevent inhalation of airborne contaminants.
Unusual Fire/Explosion	: Carbon dioxide (CO2), carbon monoxide (CO), oxides of nitrogen
Hazards	(NOx), other hazardous materials, and smoke are all possible.
	5. ACCIDENTAL RELEASE MEASURES
Personal precautions	: Wear appropriate personal protection during cleanup, such as impervious gloves, boots and coveralls.
Environmental precautions	: Should not be released into the environment. The product should no be allowed to enter drains, water courses or the soil.
Methods for cleaning up	: Clean up promptly by sweeping or vacuum. Package all material in plastic, cardboard or metal containers for disposal. Refer to Section 1 of this MSDS for proper disposal methods.
	7. HANDLING AND STORAGE
Handling	: Take measures to prevent the build up of electrostatic charge Heat only in areas with appropriate exhaust ventilation.
Storage	: Keep containers dry and tightly closed to avoid moisture absorption



MATERIAL SAFETY DATA SHEET **PG 48093 RD PP**

Version Number 1.0 Revision Date 01/09/2004 Page 3 of 6 Print Date 11/13/2011

Eye/Face Protection : Safety glasses with side-shields. Hand protection : Protective gloves. Skin and body protection : Long sleeved clothing. Additional Protective : Safety shoes. Measures : Safety shoes. General Hygiene : Handle in accordance with good industri Wash hands before breaks and at the end Engineering measures : Heat only in areas with appropriate exha appropriate exhaust ventilation at machi Exposure limit(s) Image: Silica, amorphous, 10 mg/m3 me Weighted Average (TWA): Image: Smg/m3 PEL: Silica, amorphous, 10 mg/m3 PEL: Time Weighted Average (TWA): Time Weighted Average (TWA): Solid Support the second of the s	l place.			
Eye/Face Protection : Safety glasses with side-shields. Hand protection : Protective gloves. Skin and body protection : Long sleeved clothing. Additional Protective : Safety shoes. Measures : Handle in accordance with good industri Considerations : Handle in accordance with good industri Considerations : Heat only in areas with appropriate exhaust ventilation at machi Exposure limit(s) : Heat only in areas with appropriate exhaust ventilation at machi Exposure limit(s) : : Respi Silica, amorphous, 10 mg/m3 Time Weighted Average (TWA): Respi precipitated and gel : : Respi Silica, amorphous, 10 mg/m3 PEL: Respi Silica, amorphous, 10 mg/m3 PEL: Respi Ocon : Respi : Silica, apperance : Pellets Specific Gravit Color : : Specific Gravit Color : : Not determined Vapour density Odor : : <th>ECTION</th> <th></th>	ECTION			
Hand protection : Protective gloves. Skin and body protection : Long sleeved clothing. Additional Protective : Safety shoes. Measures : Safety shoes. General Hygiene : Handle in accordance with good industri Considerations : Heat only in areas with appropriate exhappropriate exhaust ventilation at machine Exposure limit(s) : Exposure time Exposure time Silica, amorphous, 10 mg/m3 Time Weighted Average Exposition at machine Silica, amorphous, 10 mg/m3 PEL: Respi Operative data and gel : (TWA): Respi Image: solid : Respi Silica, amorphous, 10 mg/m3 PEL: Respi Solid : : Superation rat Appearance : Pellets Specific Gravit Color : : : Not determined Vapour density Odor : : Not applicable pH Water solubility : Insoluble Insoluble Image: solubility : </th <th colspan="4">: No personal respiratory protective equipment normally required.</th>	: No personal respiratory protective equipment normally required.			
Skin and body protection : Long sleeved clothing. Additional Protective : Safety shoes. Measures : Safety shoes. General Hygiene : Handle in accordance with good industri Considerations : Wash hands before breaks and at the end Engineering measures : Heat only in areas with appropriate exha appropriate exhaust ventilation at machi Exposure limit(s) : : Exposure time Silica, amorphous, 10 mg/m3 Time Weighted Average (TWA): : precipitated and gel : (TWA): : 9. PHYSICAL AND CHEMICAL PROPERTI Form : Solid Evaporation ra Appearance : Pellets Specific Gravit Color Odor : Very faint Vapor pressure Melting Point/range : Not determined Vapour density Boiling Point: : : Insoluble IO. STABILITY AND REACTIVITY Stability : Stable. Hazardous Polymerization : Will not occur. Conditions to avoid : Ke				
Additional Protective : Safety shoes. Measures General Hygiene : Handle in accordance with good industri Considerations Wash hands before breaks and at the end Engineering measures : Heat only in areas with appropriate exha appropriate exhaust ventilation at machi Exposure limit(s) Exposure time Exposure time Silica, amorphous, 10 mg/m3 Time Weighted Average (TWA): Respi precipitated and gel 10 mg/m3 PEL: Respi Silica, amorphous, 10 mg/m3 PEL: Respi frequencipitated and gel 5 mg/m3 PEL: T Solid Evaporation ra Appearance : Pellets Specific Gravit Color : RED Bulk density Odor : Very faint Vapour density Boiling Point: : Not applicable pH Water solubility : Insoluble Insoluble Image: the stability : Stability : Stability Color : Keep away from oxidizing agents and or decomposition, do	: Protective gloves.			
Measures General Hygiene Considerations : Handle in accordance with good industri Wash hands before breaks and at the end engineering measures Engineering measures : Heat only in areas with appropriate exha appropriate exhaust ventilation at machi Exposure limit(s) <u>Components</u> <u>Components</u> <u>Value</u> <u>Silica, amorphous, precipitated and gel</u> <u>Time Weighted Average (TWA):</u> <u>Silica, amorphous, precipitated and gel</u> <u>5 mg/m3</u> <u>J 5 mg/m3</u> <u>PEL:</u> <u>Solid</u> <u>Evaporation ra</u> <u>Appearance</u> <u>Color</u> : Solid <u>Solid</u> <u>Very faint</u> Vapour density <u>Odor</u> <u>Not determined</u> <u>Vapour density</u> <u>Boiling Point:</u> Not determined <u>Vapour density</u> <u>Boiling Point:</u> <u>Not applicable</u> <u>pH</u> <u>Hazardous Polymerization</u> <u>Stability</u> <u>Stability</u> <u>Stable</u> .	: Long sleeved clothing.			
Considerations Wash hands before breaks and at the end Engineering measures : Heat only in areas with appropriate exha appropriate exhaust ventilation at machi Exposure limit(s) Components Value Exposure time Exposure limit(s) Components Value Exposure time Exposure time Exp	: Safety shoes.			
appropriate exhaust ventilation at machi Exposure limit(s) 		afety practice.		
ComponentsValueExposure timeExSilica, amorphous, precipitated and gel10 mg/m3Time Weighted Average (TWA):5 mg/m3PEL:Respi15 mg/m3PEL:T9. PHYSICAL AND CHEMICAL PROPERTIForm:SolidAppearance:PelletsColor:REDBulk densityOdorOdor:Very faintVapour densityBoiling Point:Boiling Point::Not applicablepHWater solubility:InsolubleInsolubleConditions to avoid:Keep away from oxidizing agents and op decomposition, do not overheat.		Provide		
Silica, amorphous, precipitated and gel 10 mg/m3 Time Weighted Average (TWA): precipitated and gel 5 mg/m3 PEL: Respi 15 mg/m3 PEL: T 9. PHYSICAL AND CHEMICAL PROPERTI Form : Solid Evaporation ra Appearance : Pellets Specific Gravit Color : RED Bulk density Odor : Very faint Vapor pressure Melting point/range : Not determined Vapour density Boiling Point: : Not applicable pH Water solubility : Insoluble 10. STABILITY AND REACTIVITY Stability : Stable. Hazardous Polymerization : Will not occur. Conditions to avoid : Keep away from oxidizing agents and op decomposition, do not overheat.				
Silica, amorphous, precipitated and gel10 mg/m3 mg/m3Time Weighted Average (TWA):5 mg/m3PEL:Respi15 mg/m3PEL:T9. PHYSICAL AND CHEMICAL PROPERTIForm:SolidAppearance:PelletsColor:REDBulk densityOdorOdor:Very faintVapor pressureMelting point/range:Not determinedVapour densityBoiling Point::Insoluble10. STABILITY AND REACTIVITYStability:Stable.Hazardous Polymerization:Will not occur.Conditions to avoid:Keep away from oxidizing agents and op decomposition, do not overheat.	xposure type	List:		
5 mg/m3PEL:Respi15 mg/m3PEL:T9. PHYSICAL AND CHEMICAL PROPERTIForm: SolidEvaporation ratAppearance: PelletsSpecific GravitColor: REDBulk densityOdor: Very faintVapor pressureMelting point/range: Not determinedVapour densityBoiling Point:: Not applicablepHWater solubility: InsolubleIO. STABILITY AND REACTIVITYStability: Stable.Hazardous Polymerization: Will not occur.Conditions to avoid: Keep away from oxidizing agents and op decomposition, do not overheat.	Dust.	ACGIH		
9. PHYSICAL AND CHEMICAL PROPERTI Form : Solid Evaporation rate Appearance : Pellets Specific Gravit Color : RED Bulk density Odor : Very faint Vapor pressure Melting point/range : Not determined Vapour density Boiling Point: : Not applicable pH Water solubility : Insoluble 10. STABILITY AND REACTIVITY Stability : Stable. Hazardous Polymerization : Will not occur. Conditions to avoid : Keep away from oxidizing agents and or decomposition, do not overheat.	virable fraction.	OSHA Z1		
Form: SolidEvaporation raiAppearance: PelletsSpecific GravitColor: REDBulk densityOdor: Very faintVapor pressureMelting point/range: Not determinedVapour densityBoiling Point:: Not applicablepHWater solubility: InsolubleIO. STABILITY AND REACTIVITYStability: Stable.Hazardous Polymerization: Will not occur.Conditions to avoid: Keep away from oxidizing agents and op decomposition, do not overheat.	Total dust.	OSHA Z1		
Form: SolidEvaporation radionalAppearance: PelletsSpecific GravitColor: REDBulk densityOdor: Very faintVapor pressureMelting point/range: Not determinedVapour densityBoiling Point:: Not applicablepHWater solubility: InsolubleIO. STABILITY AND REACTIVITYStability: Stable.Hazardous Polymerization: Will not occur.Conditions to avoid: Keep away from oxidizing agents and op decomposition, do not overheat.	IFS			
Appearance:PelletsSpecific GravitColor:REDBulk densityOdor:Very faintVapor pressureMelting point/range:Not determinedVapour densityBoiling Point::Not applicablepHWater solubility:InsolubleInsolubleInsolubleEACTIVITYStability:Stable.Hazardous Polymerization:Will not occur.Conditions to avoid:Keep away from oxidizing agents and op decomposition, do not overheat.				
Color:REDBulk densityOdor:Very faintVapor pressureMelting point/range:Not determinedVapour densityBoiling Point::Not applicablepHWater solubility:InsolubleInsolubleInsolubleIt stabilityStability:Stable.Hazardous Polymerization:Will not occur.Conditions to avoid:Keep away from oxidizing agents and op decomposition, do not overheat.	Evaporation rate : Not applicable			
Odor : Very faint Vapor pressure Melting point/range : Not determined Vapour density Boiling Point: : Not applicable pH Water solubility : Insoluble Insoluble IO. STABILITY AND REACTIVITY Stability : Stable. Hazardous Polymerization : Will not occur. Conditions to avoid : Keep away from oxidizing agents and op decomposition, do not overheat.	Specific Gravity: : Not determined Bulk density : Not established			
Melting point/range : Not determined Vapour density Boiling Point: : Not applicable pH Water solubility : Insoluble PH 10. STABILITY AND REACTIVITY Stability : Stable. Hazardous Polymerization : Will not occur. Conditions to avoid : Keep away from oxidizing agents and op decomposition, do not overheat.		applicable		
Boiling Point: : Not applicable pH Water solubility : Insoluble 10. STABILITY AND REACTIVITY Stability : Stable. Hazardous Polymerization : Will not occur. Conditions to avoid : Keep away from oxidizing agents and op decomposition, do not overheat.		applicable		
Water solubility : Insoluble 10. STABILITY AND REACTIVITY Stability : Stable. Hazardous Polymerization : Will not occur. Conditions to avoid : Keep away from oxidizing agents and op decomposition, do not overheat.		applicable		
Stability : Stable. Hazardous Polymerization : Will not occur. Conditions to avoid : Keep away from oxidizing agents and op decomposition, do not overheat.				
Stability : Stable. Hazardous Polymerization : Will not occur. Conditions to avoid : Keep away from oxidizing agents and op decomposition, do not overheat.				
Hazardous Polymerization : Will not occur. Conditions to avoid : Keep away from oxidizing agents and op decomposition, do not overheat.				
Conditions to avoid : Keep away from oxidizing agents and op decomposition, do not overheat.				
decomposition, do not overheat.				
Incompatible Materials : Incompatible with strong acids and oxid	open flame. To a	woid thermal		
	dizing agents.			



MATERIAL SAFETY DATA SHEET

PG 48093 RD PP

Version Number 1.0 Revision Date 01/09/2004

Page 4 of 6 Print Date 11/13/2011

Hazardous decomposition products

: Carbon dioxide (CO2), carbon monoxide (CO), oxides of nitrogen (NOx), other hazardous materials, and smoke are all possible.

11. TOXICOLOGICAL INFORMATION

This mixture has not been evaluated as a whole for health effects. Exposure effects listed are based on existing health data for the individual components which comprise the mixture.

Toxicity Overview

This product contains the following components which in their pure form have the following characteristics:

CAS-No.		nical Name	Effect	Target Organ	
112926-00-8	Silica, amo precipitate		Irritant	Respiratory system, Eyes.	
	1	2. ECOLOGICA	L INFORMATIO	N	
Persistence and degrada	bility :	Not readily bio	degradable.		
Environmental Toxicity		: Chemicals are not readily available as they are bound within the matrix of the polymer.			
Bioaccumulation Potent	ial :	Chemicals are r of the polymer.		as they are bound within the matrix	
Additional advice	:	No data availab	le		
	1	3. DISPOSAL C	ONSIDERATION	S	
Product	:	possible recycli generator of wa classification, tr	ng is preferred to di ste material has the ransportation and di	e product can be recycled. Where isposal or incineration. The responsibility for proper waste sposal in accordance with and local regulations.	
Contaminated packaging		: Recycling is preferred when possible. The generator of waste material has the responsibility for proper waste classification, transportation and disposal in accordance with applicable federal, state/provincial and local regulations.			
		14. TRANSPOR	T INFORMATION	N	
U.S. DOT Classification	n :	Not regulated for	or transportation.		
ICAO/IATA (air)	:	Refer to specifi	c regulation.		
IMO / IMDG (maritime) :	Refer to specifi	c regulation.		



MATERIAL SAFETY DATA SHEET **PG 48093 RD PP**

Version Number 1.0 Revision Date 01/09/2004 Page 5 of 6 Print Date 11/13/2011

	15	. REGULATORY INFORMATION
US Regulations:		
OSHA Status	:	Classified as hazardous based on components.
TSCA Status	:	All components of this product are listed on or exempt from the TSCA Inventory.
US. EPA CERCLA Hazardous	Subs	stances (40 CFR 302)
Not applicable		
California Proposition 65	:	This product does not contain a substance listed by California Prop 65
SARA Title III Section 302 Ext	reme	ely Hazardous Substance
Not applicable		
SARA Title III Section 313 Tox	kic C	Chemicals:
Not applicable Canadian Regulations:		
National Pollutant Release	se Ir	iventory (NPRI)
Not applicable		
WHMIS Classification	:	Not controlled.
DSL	:	All components of this product are on the Canadian Domestic Substances List (DSL) or are exempt.
National Inventories:		
Australia AICS	:	Listed
China IECS	:	Listed
Europe EINECS	:	Listed
Europe Envices		
Japan ENCS	:	Not determined



MATERIAL SAFETY DATA SHEET

PG 48093 RD PP

Version Number 1.0 Revision Date 01/09/2004 Page 6 of 6 Print Date 11/13/2011

Philippines PICCS : Listed

16. OTHER INFORMATION

The information provided in this Safety Data Sheet is correct to the best of our knowledge, information and belief at the date of its publication. The information given is designed only as a guidance for safe handling, use, processing, storage, transportation, disposal and release and is not to be considered a warranty or quality specification. The information relates only to the specific material designated and may not be valid for such material when used in combination with any other materials and/or in any particular process or processing conditions.