MATERIAL SAFETY DATA SHEET

BROWN 174C

Version Number 1.0 Revision Date 10/05/2004 Page 1 of 6 Print Date 11/16/2011

1. PRODUCT AND COMPANY IDENTIFICATION

POLYONE CORPORATION 33587 Walker Road, Avon Lake, OH 44012

Telephone Emergency telephone number	:	Product Stewardship (440) 930-1395 CHEMTREC 1-800-424-9300 (24hrs for spill, leak, fire, exposure or accident).
Product name	:	BROWN 174C
Product code	:	CC10059817
Chemical Name	:	Mixture
CAS-No.	:	Mixture
Product Use	:	Industrial Applications

2. COMPOSITION/INFORMATION ON REGULATED INGREDIENTS

Components	CAS-No.	Weight %
Titanium dioxide	13463-67-7	5 - 10

3. HAZARDS IDENTIFICATION

EMERGENCY OVERVIEW

This mixture has not been evaluated as a whole. Information provided on the health effects of this product is based on individual components. All ingredients are bound and potential for hazardous exposure as shipped is minimal. However, some vapors may be released upon heating and the end-user (fabricator) must take the necessary precautions (mechanical ventilation, respiratory protection, etc.) to protect employees from exposure.

POTENTIAL HEALTH EFFECTS

Routes of Exposure:	: Inhalation, Ingestion, Skin contact			
Acute exposure				
Inhalation	: Particulates, like other inert materials can be mechanically irritating. If overheated or burnt, the polymer releases formaldehyde.			
Ingestion	: May be harmful if swallowed.			
Eyes	: Particulates, like other inert materials can be mechanically irritating.			
Skin	: Experience shows no unusual dermatitis hazard from routine handling.			
Chronic exposure	: Refer to Section 11 for Toxicological Information.			
Medical Conditions Aggravated by Exposure:	: None known.			



MATERIAL SAFETY DATA SHEET **BROWN 174C**

Version Number 1.0 Revision Date 10/05/2004 Page 2 of 6 Print Date 11/16/2011

	4. FIRST AID MEASURES
Inhalation	: Move to fresh air in case of accidental inhalation of fumes from overheating or combustion. When symptoms persist or in all cases of doubt seek medical advice.
Ingestion	: Do not induce vomiting without medical advice. When symptoms persist or in all cases of doubt seek medical advice.
Eyes	: Rinse immediately with plenty of water, also under the eyelids, for at least 15 minutes. If eye irritation persists, seek medical attention.
Skin	: Wash off with soap and plenty of water. If skin irritation persists seel medical attention.
	5. FIRE-FIGHTING MEASURES
Flash point	: Not applicable
Flammable Limits	
Upper explosion limit	: Not applicable
Lower explosion limit	: Not applicable
Autoignition temperature	: Not applicable
Suitable extinguishing media	: Carbon dioxide blanket, water spray, dry powder, foamnone.
Special Fire Fighting Procedures	: Fullface self-contained breathing apparatus (SCBA) used in positive pressure mode should be worn to prevent inhalation of airborne contaminants.
Unusual Fire/Explosion Hazards	: Carbon dioxide (CO2), carbon monoxide (CO), oxides of nitrogen (NOx), other hazardous materials, and smoke are all possible. If overheated or burnt, the polymer releases formaldehyde. May burn with invisible flame.
	6. ACCIDENTAL RELEASE MEASURES
Personal precautions	: Wear appropriate personal protection during cleanup, such as impervious gloves, boots and coveralls.
Environmental precautions	: Should not be released into the environment. The product should not be allowed to enter drains, water courses or the soil.
Methods for cleaning up	: Clean up promptly by sweeping or vacuum. Package all material in plastic, cardboard or metal containers for disposal. Refer to Section 12 of this MSDS for proper disposal methods.
	7. HANDLING AND STORAGE
Handling	: Take measures to prevent the build up of electrostatic charge. Open container only in a well-ventilated area. Heat only in areas with



MATERIAL SAFETY DATA SHEET BROWN 174C

ion Number 1.0 sion Date 10/05/2004				Print D	Page 0ate 11/16
	aj	ppropriate exhaust ver	ntilation.		
Storage		eep containers dry an nd contamination. Ke		closed to avoid moisture ry, cool place.	e absorption
8. H	XPOSURE	CONTROLS / PERS	SONAL	PROTECTION	
Respiratory protection	W in po	When temperatures exc nadequate to maintain	ceed 230° concentr	ve equipment normally °C (446°F) and ventilati ations below exposure 1 Air purifying respirators	on is imits, use a
Eye/Face Protection		afety glasses with side or abnormal processin		. Wear face-shield and j ns.	protective su
Hand protection	: P	rotective gloves.			
Skin and body protection	: L	ong sleeved clothing.			
Additional Protective Measures	: S	afety shoes.			
General Hygiene Considerations				industrial hygiene and s at the end of workday.	afety practio
Engineering measures		leat only in areas with ppropriate exhaust ver		iate exhaust ventilation. at machinery.	Provide
Exposure limit(s)					
Components	Value	Exposure time	9	Exposure type	List:
Titanium dioxide	10 mg/m3	Time Weighted Av		Exposure type	ACGIH
	U	(TWA):	e		
	15 mg/m3	PEL:		Total dust.	OSHA Z
	9. PHYSI(CAL AND CHEMIC	AL PRO	PERTIES	
E.	0.1	1	Г		
Form Appearance	: Solid	i ets, slabs			applicable determined
Color	: BRO		Bulk d	·	established
Odor		aldehyde		2	applicable
Melting point/range	: Not c	determined		r density : Not	applicable
Boiling Point:		applicable	рН	: Not	applicable
	: Insol	udie			
Water solubility					
Water solubility	10. S	STABILITY AND R	EACTIV	ITY	



MATERIAL SAFETY DATA SHEET BROWN 174C

Version Number 1.0 Revision Date 10/05/2004

Page 4 of 6 Print Date 11/16/2011

Hazardous Polymerization	:	Will not occur.
Conditions to avoid	:	Maintain polymer temperature below 230°C (446°F). Avoid prolonged exposure at or above recommended processing temperature.
Incompatible Materials	:	Incompatible with strong oxidizers and with strong acids and bases (decomposes to form formaldehyde). At melt temperatures, acetal resins are incompatible with halogenated polymers such as vinyl (PVC) and any elastomers containing any halogenated polymers. At processing conditions, these materials are mutually destructive and involve rapid degradation. Even small amounts of such contaminants can cause sudden and spontaneous formaldehyde gas formation. Workplace fume well above threshold levels are a likely result. Unsafe pressurization of equipment such as extruder or mold can also result. Thoroughly purge and mechanically clean processing equipment to avoid even trace quantities of halogenated materials from coming in contact with the acetal. Prevent contamination of virgin or rework resin.
Hazardous decomposition products	:	Carbon dioxide (CO2), carbon monoxide (CO), oxides of nitrogen (NOx), other hazardous materials, and smoke are all possible. If overheated or burnt, the polymer releases formaldehyde. Decomposition of this material depends on the lenght of time it is exposed to elevated temperatures. At the recommended processing temperature of 210°C-220°C (410°F-428°F), decomposition should not be significant until after 30 minutes. Decomposition may be accelerated by contaminants, pigments and/or other additives.

11. TOXICOLOGICAL INFORMATION

This mixture has not been evaluated as a whole for health effects. Exposure effects listed are based on existing health data for the individual components which comprise the mixture.

<u>Toxicity Overview</u> This product contains the following components which in their pure form have the following characteristics:

CAS-No.	Chemical Name	Effect	Target Organ
13463-67-7	Titanium dioxide	Systemic effects	Respiratory system.

12. ECOLOGICAL INFORMATION

Persistence and degradability	:	Not readily biodegradable.
Environmental Toxicity	:	Chemicals are not readily available as they are bound within the polymer matrix.
Bioaccumulation Potential	:	Chemicals are not readily available as they are bound within the polymer matrix.



MATERIAL SAFETY DATA SHEET **BROWN 174C**

Version Number 1.0 Revision Date 10/05/2004 Page 5 of 6 Print Date 11/16/2011

Additional advice	: Not applicable
	13. DISPOSAL CONSIDERATIONS
Product	: Like most thermoplastic plastics the product can be recycled. Where possible recycling is preferred to disposal or incineration. The generator of waste material has the responsibility for proper waste classification, transportation and disposal in accordance with applicable federal, state/provincial and local regulations.
Contaminated packaging	: Recycling is preferred when possible. The generator of waste material has the responsibility for proper waste classification, transportation and disposal in accordance with applicable federal, state/provincial and local regulations.
	14. TRANSPORT INFORMATION
U.S. DOT Classification	: Not regulated for transportation.
ICAO/IATA (air)	: Refer to specific regulation.
IMO / IMDG (maritime)	: Refer to specific regulation.
	15. REGULATORY INFORMATION
US Regulations:	
OSHA Status	: Classified as hazardous based on components.
TSCA Status	: All components of this product are listed on or exempt from the TSCA Inventory.
US. EPA CERCLA Hazardous	Substances (40 CFR 302)
Not applicable	
California Proposition 65	: This product does not contain a substance listed by California Prop 65.
SARA Title III Section 302 Ext	remely Hazardous Substance
Not applicable	
SARA Title III Section 313 Tox	cic Chemicals:
Not applicable	

PolyOne

MATERIAL SAFETY DATA SHEET **BROWN 174C**

Version Number 1.0	
Revision Date 10/05/2004	

_

Page 6 of 6 Print Date 11/16/2011

Canadian Regulations:			
National Pollutant Relea	ise Ii	ventory (NPRI)	
Not applicable			
WHMIS Classification	:	Not controlled.	
DSL	:	All components of this product are on the Canadian Domestic Substances List (DSL) or are exempt.	
National Inventories:			
Australia AICS	:	Listed	
China IECS	:	Listed	
Europe EINECS	:	Not determined	
Japan ENCS	:	Not determined	
Korea KECI	:	Listed	
Philippines PICCS	:	Listed	
		16. OTHER INFORMATION	T

The information provided in this Safety Data Sheet is correct to the best of our knowledge, information and belief at the date of its publication. The information given is designed only as a guidance for safe handling, use, processing, storage, transportation, disposal and release and is not to be considered a warranty or quality specification. The information relates only to the specific material designated and may not be valid for such material when used in combination with any other materials and/or in any particular process or processing conditions.